

A-TECH 260

TWO COMPONENT, SOLVENT FREE, HIGH SOLIDS URETHANE ELASTOMERIC BASE MEMBRANE USED FOR A VARIETY OF INTERIOR/EXTERIOR APPLICATIONS

CURING

At 70°F (21°C) and 50% relative humidity, allow each coat to cure for 2-4 hours before proceeding subsequent coats.

EQUIPMENT CLEANUP

Equipment should be cleaned with an environmentally safe, urethane-grade solvent (alcohol free) as permitted under local regulations immediately after use.

STORAGE

A-TECH 260 has a shelf life of one (1) year from date of manufacture in factory-sealed containers.

LIMITATIONS

- Do not open until ready to use.
- Product must be mixed in ratio
- A-TECH 260 must be top coated with A-Tech 295

MIXING

A-TECH 260 may not be diluted under any circumstances. Proportions are premeasured. Using a mechanical mixer, first pre-mix separately Part-A and Part-B base material thoroughly to

TECHNICAL DATA (Based on draw down film)

Solids by Volume.....	95%
Pot Life (min @ 75°F, 50% RH).....	15 ± 3 minutes
Tack Free Time.....	4-6 hours
Hardness, ASTM D-2240.....	.64 ± 3 A
Tensile Strength, ASTM D-412.....	1500 ± 100 psi
Elongation, ASTM D-412.....	1000 ± 100%
Tear, ASTM D-624.....	230 ± 25 pli
Split Tear, ASTM D-470.....	.60 ± 5 pli
Total Solids by Volume, ASTM D-2697.....	95%
Volatile Organic Compounds*	
ASTM D-2369-81.....	0.46 lb/gal 55 gm/liter

* Contains some high boiling colorless plasticizers.

**Manufactured In The United States Of America Exclusively For
A-Tech Products & Services Ltd.
#45 Petite Café, Princes Town
Trinidad West Indies
1-868-655-8395 / 1-868-354-5509**

- A-TECH 260 cannot withstand direct wear and abrasion.
- The following substrates must not be coated with A-TECH deck coating systems or products: on grade or below grade slabs, split slabs with buried membrane, sandwich slabs with insulation, slabs over unvented metal pan, suspended pool decks, swimming pools, magnesite, lightweight concrete, asphalt surfaces and asphalt overlays.

WARNING

This product contains Isocyanates and Curative Material.

**For technical assistance call
1-868-655-8395**

LIMITED WARRANTY

The manufacturer guarantees its products to be free of defects and the extent of its liability is limited to the purchase price of the materials only, if proved to be defective. Improper mixing, incorrect application or other factors beyond the control of the manufacturer or its dealers may produce unsatisfactory results and cannot be held to be the manufacturers or its dealers responsibility. There are no other guarantees either expressed or implied.

05/01/2010

**A-Tech Products & Services Ltd.
#45 Petite Café, Princes Town
Trinidad West Indies
1-868-655-8395 / 1-868-354-5509**